

SUMMIT CAP

Mass per unit area: EN 12127:1997	164 g/m ²	± 10 %
Air Permeability EN ISO 9237:1995	40,34 mm/s	± 10 %
Thermal Resistance (RCT): EN ISO 11092:2014	0,0132 m ² K/W	± 10 %
Water Vapour Resistance (RET): EN ISO 11092:2014	3,61 m ² Pa/W	± 10 %
Bursting resistance: EN ISO 13938-1:2019	406 kPa	± 10 %
Determination of dimensional change in domestic washing and drying:		
EN ISO 5077:2008	LENGTHWISE < ±3%	CROSSWISE < ±3%
	Washing procedure 3N (Ta=30 ±3°C) according to ISO 6330:2012	
Resistance to pilling: ISO 12945-2:2000	5	2000 CYCLES
Scale from 1 to 5 in which 1 is "Very severe pilling" and 5 is "No pilling".		
Fastness rates:		
Colour fastness to domestic and commercial laundering: EN ISO 105-C06:2010		4 - 5 *
Colour fastness to perspiration (Alkaline & Acid): EN ISO 105-E04:2013	ALKALINE	4 *
	ACID	4 *
Colour fastness to rubbing (Dry & Wet): EN ISO 105-X12:2016	DRY	4 - 5 *
	WET	4 - 5 *
Colour fastness to sea water: EN ISO 105-E02:2013		4 *
* Fastness rates in a scale from 1 to 5 in which 1 is "Poor behaviour" and 5 is "Good behaviour".		
** Fastness to artificial light rates in a scale from 1 to 8 in which 1 is "Very poor" and 8 is "Excellent"		